

B I S F A

THE INTERNATIONAL BUREAU
FOR THE STANDARDISATION OF MAN-MADE FIBRES

Testing methods for polyester filament yarns

2004 - Edition
(This edition replaces the 1995 edition)

SCOPE

These methods apply to polyester (polyethylene terephthalate, polybutylene terephthalate) filament yarns and various derived products:
single yarns (including POY),
interlaced yarns,
multiple wound yarns,
folded yarns,
cabled yarns,
yarns on beams,
monofilament
special fabrics (but excluding textured filament yarns and tows for staple fibre) destined for either textile or industrial use.

Note: that separate booklets apply for Polyester Staple and textured yarn.
Appendix I sets out the definitions of polyester to which these methods apply.

© BISFA 2004

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission from the publisher.

BISFA
Avenue E. Van Nieuwenhuysse 4
B - 1160 Brussels
Belgium
Email: tun@cirfs.org
Website: <http://www.bisfa.org>

CONTENTS

	Page
Scope	2
Introduction	10
Preface	11
Chapter 1	12
GENERAL RULES FOR SETTLING OF DISPUTES	
Chapter 2	14
DEFINITIONS	
Chapter 3	24
SAMPLING	
3.1	24
General remarks	
3.2	24
Taking the consignment sample and the number of containers to be sampled	
3.3	25
Taking the laboratory samples for determination of commercial mass	
3.3.1	25
Determination of invoice mass and gross mass of the consignment sample	
3.3.2	25
Taking packages from the containers of the consignment sample	
3.3.3	26
Determination of the net mass of sampled containers	
3.4	26
Taking laboratory samples for determination of properties other than commercial mass	
3.4.1	26
Packages to be used as laboratory samples	
3.5	26
Sampling and determination of commercial mass of tyre cord fabrics	
3.5.1	26
Preparing the tabby samples	
3.5.2	27
Preparing the laboratory samples for determination of commercial mass	
3.6	27
Sampling for determinations other than of commercial mass	
Chapter 4	29
DETERMINATION OF COMMERCIAL MASS	
4.1	29
Scope	
4.2	29
Principle	
4.2.1	29
Conventional allowance	
4.3	29
Apparatus, materials and reagents	

4.3.1	Apparatus and materials	29
4.3.2	Reagents	30
4.4	Test procedure	30
4.4.1.1	Preparing the laboratory samples and test specimens of commercial mass	30
4.4.2	Operating conditions	31
4.4.3	Determining the mass of the test specimen	31
4.4.4	Cleaning of test specimens	31
4.4.5	Determining the over-dry mass of the test specimens	32
4.4.6	Data to be collected	32
4.5	Calculation of results and statistical evaluation	32
4.5.1	Calculation of properties	32
4.5.2	Statistical evaluation	33
4.6	Determination of the commercial mass of tyre cord fabrics	33
4.6.1	Determination of the commercial mass of undipped fabrics	33
4.6.2	Determination of the commercial mass of dipped fabrics	34
4.6.3	Verification factor of consignment of tyre cord fabric	34
4.7	Determination of the commercial mass of unsized and sized yarns on beams	34
4.8	Verification of invoice mass	35
4.9	Presentation of results	35
4.10	Example of verification of invoiced mass	35
4.10.1	General	35
4.10.2	Consignment to be verified	35
4.10.3	Collect data	35
4.10.4	Calculations	37
4.10.5	Verification of invoiced mass	38
Chapter 5	DETERMINATION OF TWIST	39
5.1	Scope	39
5.2	Principle	39
5.3	Apparatus	39
5.3.1	Instrument	39
5.3.2	Auxiliary devices	40
5.4	Test procedure	40
5.4.1	Operating conditions	40
5.4.2	Preparing the test specimens and performing the test for single yarns	40
5.4.3	Testing folded yarn	41
5.4.4	Testing tyre cord fabrics	42

5.5	Data to be collected	42
5.6	Calculation of results and number of tests	42
5.6.1	Calculation of properties	42
5.6.2	Statistical evaluation	42
5.7	Designation of yarns	43
5.8	Presentation of results	43
5.9	Tolerance	44
Chapter 6	DETERMINATION OF LINEAR DENSITY	45
6.1	Scope	45
6.2	Principle	45
6.3	Apparatus	45
6.3.1	Skein winding reel	45
6.3.2	Balance	45
6.4	Test procedure	46
6.4.1	Pretension	46
6.4.2	Preparing the test specimens and performing the test	46
6.4.3	Data to be collected	47
6.4.4	Calculation of properties	47
6.5	Testing the linear density of dipped yarns	47
6.6	Testing the linear density of yarns from tyre cord fabric	48
6.6.1	Sampling of consignments of fabrics	48
6.6.2	Testing linear density of yarns from undipped fabric	48
6.6.3	Testing linear density of yarns from dipped fabric	48
6.7	Calculation of properties and statistical evaluation	48
6.7.1	Calculation of properties	48
6.7.2	Statistical evaluation	49
6.8	Presentation of results	49
6.9	Tolerance	49
Chapter 7	TENSILE PROPERTIES	51
7.1	Scope	51
7.2	Principle	51
7.3	Apparatus	51
7.3.1	Tensile tester	51
7.3.2	Clamps	52

7.3.3	General testing facilities	54
7.4	Preparation of laboratory sample	54
7.4.1	Consignment of filament yarns and cords	54
7.4.2	Consignments of tyre yarn fabrics	55
7.5	Test procedure	55
7.5.1	Operating conditions	55
7.5.2	Preparation of test specimen and loading procedure	56
7.5.3	Performance of test	58
7.5.4	Number of tests	58
7.5.5	test deficiencies	58
7.5.6	Modifications to the test procedure	58
7.5.7	Data to be collected	58
7.6	Calculation of properties and statistical evaluation	59
7.6.1	Calculation of properties	59
7.6.2	statistical evaluation	60
7.7	Presentation of results	60
7.8	Tolerance	61
Chapter 8	DETERMINATION OF AMOUNT OF DIP	62
8.1	Scope	62
8.2	Principle	62
8.3	Apparatus	62
8.3.1	The apparatus to be used and its accuracy	62
8.3.2	Reagents	62
8.4	Test procedure	62
8.4.1	Preparing samples	62
8.4.2	Removal of the yarn	63
8.4.3	Data to be collected	63
8.5	Calculation of results	63
8.6	Presentation of results	64
8.7	Tolerance	64
Chapter 9	DETERMINATION OF BOILING WATER SHRINKAGE	65
9.1	Scope	65
9.2	Principle	65

9.3	Apparatus	65
9.3.1	Skein-winding reel	65
9.3.2	Length measuring stand	65
9.3.3	Water vessel	65
9.3.4	Additional means	66
9.4	Test procedure	66
9.4.1	Operating conditions	66
9.4.2	Preparing the test specimens	66
9.4.3	Measuring the initial length of the test specimens	67
9.4.4	Thermal treatment of the test specimens	67
9.4.5	Measuring the length of the test specimens after treatment	68
9.4.6	Data to be collected	68
9.5	Calculation of results and statistical evaluation	68
9.5.1	Calculation of properties	68
9.5.2	Statistical evaluation	68
9.5.3	Number of additional tests of laboratory samples	68
9.6	Presentation of results	69
9.7	Tolerance	69
Chapter 10	DETERMINATION OF HOT-AIR SHRINKAGE (After Treatment)	70
10.1	Scope	70
10.2	Principle	70
10.3	Apparatus	70
10.3.1	Skein-winding reel	70
10.3.2	Length measuring stand	70
10.3.3	Ventilated oven for temperature up to 250°C	70
10.3.4	Additional means	71
10.4	Test procedure	71
10.4.1	Operating conditions	71
10.4.2	Preparing the test specimens	71
10.4.3	Measuring the initial length of the test specimens	71
10.4.4	Thermal treatment of the test specimens	72
10.4.5	Measuring the length of the test specimens after treatment	72
10.4.6	Data to be collected	72
10.5	Calculation of properties and statistical evaluation	72
10.5.1	Calculation of shrinkage	72
10.5.2	Statistical evaluation	73
10.5.3	Number of additional tests of laboratory samples	73

10.6	Presentation of results	73
10.7	Tolerance	73
Chapter 11	DETERMINATION OF HOT-AIR SHRINKAGE (During Treatment)	74
11.1	Scope	74
11.2	Principle	74
11.3	Apparatus	74
11.3.1	Skein-winding reel	74
11.3.2	Heating unit, for temperatures up to 250 °C	74
11.3.3	Length device integrated into a heating unit	74
11.4	Test procedure	75
11.4.1	Operating conditions	75
11.4.2	Preparing the test specimens	75
11.4.3	Setting the initial length of the test specimen	76
11.4.4	Thermal treatment of the test specimen	76
11.4.5	Measuring the hot air shrinkage (HAS) of the test specimen during treatment	76
11.4.6	Number of test specimen	77
11.4.7	Data to be collected	77
11.5	Calculation of properties and statistical evaluation	77
11.5.1	Statistical evaluation	77
11.5.2	Number of additional tests of laboratory samples	77
11.6	Presentation of results	77
11.7	Tolerance	78
Chapter 12	DRAWING PROPERTIES OF POY	79
12.1	Scope	79
12.2	Principle	79
12.3	Definitions	79
12.4	Apparatus	79
12.4.1	Instrument	79
12.4.2	Heating unit	80
12.4.3	General testing facilities	80
12.5	Preparation of laboratory sample	80

12.5.1	Consignment of POY-filament yarns	80
12.6	Test procedure	80
12.6.1	Operating conditions	80
12.6.2	Preparation of test specimen and loading procedure	81
12.6.3	Performance of test	81
12.6.4	Yarn breaks during test performance	81
12.6.5	Modifications to the test procedure	81
12.6.6	Data to be collected	82
12.7	Calculation of results and number of test	82
12.7.1	Measured values	82
12.7.2	Derived variables	82
12.7.3	Number of tests	82
12.8	Presentation of results	82
Chapter 13	THE STATISTICS: TERMINOLOGY AND CALCULATIONS	84
13.1	Definitions	84
13.2	Basic Statistics	85
13.2.1	Individual value	85
13.2.2	Frequency distribution	85
13.2.3	Frequency	85
13.2.4	Arithmetic mean	86
13.2.5	Overall arithmetic mean	86
13.2.6	Variance and standard deviation	86
13.2.7	Coefficient of variation	87
13.2.8	Confidence limits	87
13.2.9	Number of tests	88
13.3	Statistical process control (SPC)	89
13.3.1	Process capability	89
13.3.2	Accuracy index	89
13.3.3	Capability index	89
13.3.4	Quality index	89
Appendix I	DEFINITION OF POLYESTER, CHEMICAL FORMULA	91

INTRODUCTION

This booklet replaces the 1995 edition yet retains most of the original concepts, whilst taking into account further improvements in the testing procedures and a broader range of products

As it is not always easy to distinguish between yarns for textile use and yarns for industrial use, the test methods given in this booklet have been chosen such that the testing of all polyester filament yarns (other than textured yarns) is covered.

Recently BISFA has been engaged in a thorough review of its "TERMINOLOGY" booklet, particularly the list of terms used in other booklets, and their definitions. Where relevant, the new and updated terms and definitions have been incorporated in this booklet.

A thorough revision of the "Determination of Commercial Mass" has taken place to include beams and to refine the procedure.

Two options for the "Determination of Linear Density " are included in this booklet.

The general arrangement of the chapters has been made more concise and much repetition has been eliminated. Great care has been taken to make the texts as uniform as possible in presentation and in a style similar to the other BISFA booklets. The texts as a whole are easier to understand.

These improvements should ensure that the procedures recommended by BISFA in this booklet and in its other publications retain their position as the most up-to-date internationally agreed testing methods for man-made Polyester Filament Yarns and Tyre Cord Fabrics.

Acknowledgement

BISFA wishes to acknowledge and thank Mr. B. Tabor from Acordis and Mr. M Taylor from DuPont, who revised this booklet

PREFACE

One of the principal aims of BISFA as set out in its statutes is to establish for man-made fibres rules for classification and nomenclature and standard test methods to serve as a basis for sound trading practice.

The methods of manufacture used for such fibres allow a variety of new materials to be produced, and it is therefore becoming increasingly necessary to establish standardised concepts which will foster harmonious technical and commercial relationships both at the national and the international level.

As new fibre products appear, BISFA endeavours to establish suitable new rules and methods for them. These rules and methods embody concepts acceptable to producers, users and testing establishments alike. They currently describe testing methods for checking goods upon receipt and include:

- the determination of the commercial mass, linear density, and tensile properties for all products and in addition, the length for staple fibres; the shrinkage and twist for filament yarns; the amount of dip for tyre cord yarns and the antibacterial properties for bioactive fibers.
- maximum tolerances for commercial mass, and for certain other fibre related properties for example, linear density, twist, fibre length.
- the conventional allowance used for the calculation of commercial mass

The methods which BISFA advocates for measuring the above properties are described in detail in the various BISFA methods booklets for each specific fibre to enable comparable results to be obtained between laboratories.

BISFA defines the commercial mass of a consignment in a manner, which is independent of the state in which the material is delivered and, in particular, of fluctuations in the moisture content of the material. This ensures that the buyer can know within narrow technical limits what he is paying for, whatever may be the actual moisture content of the material at the time of delivery.

BISFA bases its calculation of commercial mass upon the oven-dry mass of the pure fibre material that, depending on the fibre type, is essentially free of extractable material that may be present to assist fibre processing (e.g. spin finish, lubricant, size, adhesive). The oven-dry mass is corrected by a numerical constant referred to as the conventional allowance;(see Chapter 2 Definition). For some products further corrections may apply and will be specified in the appropriate booklet.

The invoiced mass, since it is independent of the actual moisture content, is consequently often different from the mass found upon weighing the goods as delivered.

The detailing of the test methods given by BISFA would be of no value unless the samples measured could be considered as representative of the entire consignment. BISFA has, therefore, also provided a sampling procedure, dependent on the number of containers in the consignment. Consequently, the results of tests according to BISFA methods normally are valid only for the entire consignment and not for individual items such as single packages, spools, etc.

Attention is drawn to other BISFA publications, in particular the booklet "Terminology relating to man-made fibres".

Users are responsible for ensuring that the latest and complete edition of the appropriate BISFA booklet is employed.

